








Product Specifications for Tyvek® HomeWrap®

PROPERTIES	METHOD	TYVEK® HOMEWRAP®
Air Penetration	Air-Ins (cfm/ft ² @75 Pa)	.007
	Gurley Hill (TAPPI T-460) (sec/100cc)	300
	ASTM E-1677	Type 1
Water Vapor Transmission	ASTM E-96 Method B (g/m ² -24 hrs) (perms)	400 58
	Water Penetration Resistance	AATCC-127 (cm)
Basis Weight	TAPPI T-41D (oz/yd ²)	1.8
Breaking Strength	ASTM D-882 Method A (lbs/in)	30/30
Tear Resistance (trapezoid)	ASTM D-1117 (lbs)	6/6
Surface Burning Characteristics	ASTM E-84-97a Flame Spread	Class A
	Indexed Smoke Developed Value	Class A

WARNING: Tyvek® is combustible and should be protected from a flame and other high heat sources. If the temperature of Tyvek® reaches 750 F (400 C), it will burn and the fire may spread and fall away from the point of ignition.

For more information:

1-800-44-TYVEK®
www.tyvekconstruction.com




Tyvek® HomeWrap®
Build it once, build it right.