

## 1K Gun foam



### Usage

#### Installation examples

- Filling window frame gaps and around window sills
- Insulating pipes
- Filling in wall penetrations, cavities, around roller shutter boxes - use for all interior work
- Fixing and sealing in walls and ceilings

### Description

- Single-component polyurethane foam
- The foam is extruded by using a fischer PU pistol and hardens via chemical reaction with atmospheric humidity.

### Examples of use



## Installation

### Installation information

- General test certificate from building authorities: P - NDS04 - 137.
- Noise-reducing properties tested by the Institut für Fenstertechnik (Institute of Window Technology) e.V. Rosenheim (D). Refer to i.f.t. Test Report No. 169 17465 issued 8 July 1996.
- Wet base surface if atmospheric humidity is low.
- Shake cartridge before use.
- Hold valve downwards when extruding foam.
- Foam yield of extruded foam: up to 45 litres.
- Resistance to temperature of hardened foam: -30° C to +80° C.
- Non-tacky after approx. 10 minutes, can be cut after approx. 25 minutes, load-bearing after approx. 3 hours, completely hardened after approx 5 - 8 hours (all details based on temperature of +20° C).
- Extrude with PU pistol (refer to page XY).

Technical data

Type	Art.-No.	ETA ■ DIBt ●	contents per canister [ml]	shelf life months	max. foam yield (free foaming) [l]	tack free after [min]	cuttable after [min]	languages on the label		EAN Code
PUP 750 B2	53084	-	750	12	45	10	25	D	39095090	4006209530849